

DATASHEET

ACRYLIC (EXTRUDED)

Extruded acrylic sheet offers excellent thickness tolerance and is extremely easy to vacuum form, making it ideal for applications where complex shapes are required. Whereas Perspex cast is produced in small batches, extruded sheet is made by extruding acrylic polymer over longer, more economical production runs. Consequently, extruded sheet is not available in the same extensive range of colours and finishes.

Applications

- Exhibition Displays
- Glass Replacement
- Machine Guards
- Model Making
- · Point of Purchase Displays
- · Point of Sale Displays
- Poster Framing
- Print Material
- Safety Glazing
- Shelving Systems

Availability

- Colour Clear, Opal & Glass Look
- Type Sheets, Rods & Tubes
- Regularly produced in a wide variety of thicknesses

Typical Properties

| General Properties | Method | Unit | Test Result |
|-------------------------------------|-------------|---------|-------------|
| Physical Properties | | | |
| Relative Density | ISO 1183 | g/cm3 | 1.2 |
| Water Absorption | ISO 62 | % | 0.2 |
| Mechanical Properties | | | |
| Tensile Strength at Yield (5mm/min) | ISO 527 | MPa | 70 |
| Tensile Strength at Break | | | |
| Elongation at Yield | | | |
| Elongation at Break (5mm/min) | ISO 527 | % | 4 |
| Tensile Modulus of Elasticity | | | |
| Flexural Modulus (2mm/min) | ISO 178 | MPa | 3030 |
| Izod Impact Strength (notched) | ISO 180/1A | kJm-2 | N/A |
| Charpy Impact Strength (notched) | ISO 179 | | 10 |
| Charpy Impact Strength (unnotched) | ISO 179 | | N/A |
| Impact Falling Weight | | | |
| Rockwell Hardness | ISO 2039-2 | M Scale | 101 |
| Thermal Properties | | | |
| Service Temperature | | °C | -40 to 80 |
| Heat Distortion Temperature | | | |
| Vicat Softening Temperature | ISO 306 | °C | > 105 |
| Coefficient of Thermal Expansion | ASTM D-696 | Mm/m°C | 0.078 |
| Thermal Conductivity | | | |
| Specific Heat Capacity | | | |
| Optical Properties | | | |
| Light Transmission (3mm sheet) | ASTM D-1003 | % | > 92 |
| Refractive Index | ISO 489/A | | 1.49 |
| Yellowness Index | | | |
| Electrical Properties | | | |
| Dielectric Strength | IEC 243 | kV/mm-1 | 15 |
| Surface Resistivity | IEC 93 | Ω m-2 | > 10(14) |